



SealSkin™ Flashing Tape represents a high-bond tape & flashing solution that exceeds industry standards for air and water penetration. Developed specifically for high-performance enclosures, it combines the handling of traditional tapes with the durability of robust flashing systems. Flashing Tape integrates a thick, synthetic rubber adhesive with a durable yet highly conformable weave backing. It was designed with optimal handling in mind for precise application without creasing and edge folding. It also offers high initial tack while remaining repositionable until back-rolled. Intended as a general-purpose tape & flashing, it adheres to a wide range of construction materials, including air & water barriers, integrated WRB panels, facers, wood, concrete, magnesium oxide, metals, and plastics.

Advantages

- Innovative hybrid synthetic rubber formulated for high flow and strong bond
- Durable, highly conforming HDPE weave backing
- Siliconized paper release liner with back-slitting
- 100% solid, solvent-free, and low VOCs
- Hydrophobic – will not absorb or attract moisture
- UV Stability – 6 months
- Vapor, air, and water-tight
- Indefinite shelf life when maintained below 80°F
- Service temperature -40°F to 180°F (-40°C to 82°C)
- Application temperature 15°F to 120°F (-9°C to 49°C)
- Nail sealability (Tested to AAMA 711-13) Pass
- Edge sealability: 21.6" hydrostatic pressure >48 hours
- Backing is compatible with most sealants and liquid flashing products. Including MS Polymers, Silicone, Polyurethane and Butyl. (Always check adhesion)

Technical Data

*All values measured in lb/in.

PROPERTY	SUBSTRATE	VALUE*	STANDARDS
90° Peel Adhesion	OSB - Smooth Side	10.0	ASTM D3330 per AAMA 711- 13
	OSB - Rough Side	7.5	
	Plywood	12.3	
	Anodized Aluminum	14.5	
	2x4 (Douglas Fir)	15.0	
	Glass Mat Gypsum Facer	15.5	
	Foil Facer	13.8	
	SealSkin Tape Backing	14.5	
	PVC Panel	13.8	
	Acylic Panel	14.5	
	Magnesium Oxide - Uncoated	16.3	
	Magnesium Oxide - Coated	13.8	
	Zip WRB Panel	9.5	
	WeatherLogic WRB Panel	8.8	
ForceField WRB Panel	11.3		
Glass	13.5		
7-day Water Immersion 90° Peel Adhesion	Anodized Aluminum	13.5	
	SealSkin Tape Backing	15.5	
	PVC Panel	13.5	
	Acylic Panel	13.3	
	Magnesium Oxide - Uncoated	19.8	
	Magnesium Oxide - Coated	10.5	



Application Instructions

- For proper adhesion, bonding surface must be dry and free of dirt, debris, dust, dirt, frost or ice.
- When bonding to wood and porous materials, use a stiff brush or scraper to remove loose particles and debris from the bonding surface prior to application.
- Always check adhesion and chemical compatibility with any new substrate.
- Do not apply over projecting fastener heads, sharp leading edges, or other protuberances that may puncture the tape backing.
- Gradually peel back the release liner and begin applying short sections using hand pressure, working from the center out to avoid wrinkles and creasing. Overlap the tape 2"-3" at the tape joints for a tight seal.
- Back-roll with a 45 durometer roller to work the tape into the surface and to ensure proper bonding at tape edges.
- If tape does not adhere, use additional site-specific measures to assure proper adhesion.
- Cut and overlap at a minimum of 15'.

Packaging/Colors

- Colors: White or Black
- 2-1/2" x 75' 8/case
- 4" x 75' 6/case – Back-slit on center
- 6" x 75' 4/case – Back-slit on center
- 12" x 75' 2/case – Back-slit on center



WARNING: Cancer
and Reproductive Harm
www.P65Warnings.ca.gov

LIMITED WARRANTY:

Products are free from manufacturing defects and when used according to the manufacturer's published specifications will meet the manufacturer's published performance standards for a period of ten years from the date of shipment from the factory. Sustant will, at its sole option, replace the defective product or refund the purchase price paid by the user. There are no other warranties, express or implied, including but not limited to any implied warranties of merchantability or fitness for a particular purpose. The user is responsible for determining the suitability of the product for the user's needs. Neither Sustant nor its manufacturers shall have a liability for any other damages, including but not limited to any indirect, special, or consequential damages, even if they have been advised of the possibility of such.